

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78
Tel. 059 822417 r.a. - Fax 0598635115 - e-mail : info@modenacentroprove.it - www.modenacentroprove.com
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

AUTOMOTIVE

Modena, 21/07/21

To **REFIN CERAMICHE SPA**
VIA I MAGGIO NR. 22 FRAZ.
SALVATERRA
42013 CASALGRANDE RE

Attn.

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
Pocelain tiles	CORTINA ALMOND	Our withdrawal of samples	15/07/2021

Here attached, you will receive the Test Report of Serial No. **20215424**/n, which shows the results of tests required.

MODENA CENTRO PROVE

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe



TEST REPORT: 20215424/1

Modena, 21/07/21

CUSTOMER	REFIN CERAMICHE SPA - - VIA I MAGGIO NR. 22 FRAZ. SALVATERRA - 42013 - CASALGRANDE - RE
MATERIAL and/o SAMPLE to be tested	Pocelain tiles;
Denomination	CORTINA ALMOND;
Date of sample reception	15/07/2021;
Date of sample acceptance	15/07/2021;
Kind of test executed	Determination of the anti-slip properties – Wet-loaded barefoot areas; Walking method – Ramp test
Referring standards	DIN 51097:1992
Shifting from standards	No one
Equipment	Pullmeter with ramp cod. MCP C150
Subcontracted phases	No one
Sampling made by	Customer





The test results reported in this Test Report refer only to the sample sampled by our staff and / or given by the Customer as received.

The sample identification data were provided by the customer. Further additional information provided by the Customer will be reported in the Test Report in blue color. If the information provided by the customer influences the validity of the results, MCP declines all responsibility.

Any changes / additions made to the Test Report after its first issue will be identified by underlining the text.

The Customer undertakes to reproduce this document in its entirety. Any form of partial reproduction is prohibited.

The storage times of the samples are indicated on the offer or contract to which this Test Report refers.

<p>Examiner  p.i. Nasseti Luca Examiner  p.i. Bortolai Alberto</p>	<p>MODENA CENTRO PROVE  Ceramic Dept. Responsible P.I. De Pasquale Roberto</p>	<p>MODENA CENTRO PROVE  Director Sant'Unione dr. Giuseppe</p>
--	--	---



DETERMINATION OF THE ANTI-SLIP PROPERTIES – WET-LOADED BAREFOOT AREAS; WALKING METHOD – RAMP TEST

Beginning date : 16/07/2021

Analysis ending date : 19/07/2021

SAMPLE : Ceramic tiles, marked « **CORTINA ALMOND** »

RESULTS

Sample dimensions (length, width) 1x0.5 m
Width of joints 5 (mm)
Groutig substance mortar
Direction of profiles no one

SLIP ANGLE 20
CLASSIFICATION B

CLASSIFICATION

Total Average Values	Group Classification
$\geq 12^\circ$	A
$\geq 18^\circ$	B
$\geq 24^\circ$	C

Examiner

p.i. Nasseti Luca
Examiner

p.i. Bortolai Alberto

MODENA CENTRO PROVE

Ceramic Dept. Responsible
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director
Sant'Unione dr. Giuseppe